

517, 816

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
31 December 2003 (31.12.2003)

PCT

(10) International Publication Number  
**WO 2004/000455 A1**

(51) International Patent Classification<sup>7</sup>:  
C07C 51/31, 51/265

**B01J 23/22,**

(74) Agent: **RIEGLER, Norbert Hermann;** Lonza AG,  
Münchensteinerstrasse 38, CH-4052 Basel (CH).

(21) International Application Number:

PCT/EP2003/006494

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(22) International Filing Date: 19 June 2003 (19.06.2003)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:  
MI2002A001358

*14 Dec 04*  
19 June 2002 (19.06.2002) IT

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(71) Applicant (*for all designated States except US*): **LONZA SPA** [IT/IT]; Via Enrico Fermi, I-24020 Scanzorosciate (IT).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **CAVANI, Fabrizio** [IT/IT]; Via San Giovanni Bosco, 78, I-41100 Modena (IT). **FUMAGALLI, Carlo** [IT/IT]; Via Conti Albani, 2/c, I-24061 Albano Sant'Alessandro (IT). **LEANZA, Roberto** [IT/IT]; Via Val di Sole, 11, I-20141 Milano (IT). **MAZZONI, Gianluca** [IT/IT]; Via Marzanica, 1, I-24020 Torre Boldone (IT). **PANZACCHI, Barbara** [IT/IT]; Via delle Armi, 6, I-40141 Bologna (IT).

**Declaration under Rule 4.17:**

— *of inventorship (Rule 4.17(iv)) for US only*

**Published:**

— *with international search report*

*For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: **TITANIUM-VANADIUM-TIN COMPRISING CATALYST AND PROCESS FOR THE PREPARATION OF PHTHALIC ANHYDRIDE**

(57) Abstract: Disclosed are catalytic compositions comprising oxides of titanium, vanadium and tin which are suitable for the production of phthalic anhydride by oxidizing o-xylene and/or naphthalene in the gas phase. The catalysts exhibit excellent activity and selectivity. The catalyst comprise 2 to 15% by weight (calculated as V<sub>2</sub>O<sub>5</sub>) of vanadium, from 1 to 15% by weight (calculated as SnO<sub>2</sub>) of tin and further comprise from 70 to 97% by weight (calculated as TiO<sub>2</sub>) of titanium. In a preferred embodiment the catalyst of the invention comprise up to 5% by weight (calculated as M<sub>2</sub>O) of at least one alkali metal, preferably lithium, potassium or rubidium, and more preferably cesium. In an even more preferred embodiment, cesium is present in an amount of from 0.01 to 2% by weight (calculated as Cs<sub>2</sub>O).

WO 2004/000455 A1

**BEST AVAILABLE COPY**  
**BEST AVAILABLE COPY**

## TITANIUM-VANADIUM-TIN COMPRISING CATALYST AND PROCESS FOR THE PREPARATION OF PHTHALIC ANHYDRIDE

The present invention relates to a catalyst for the selective oxidation of *o*-xylene, naphthalene, or a mixture of both to phthalic anhydride in the gas-phase, using a gas  
5 containing molecular oxygen, preferably air. The catalyst is characterised by a high activity and a high selectivity to phthalic anhydride. It further relates to a process for the preparation of said catalyst and a process for the production of phthalic anhydride employing said catalyst.

10 Phthalic anhydride is an important chemical intermediate used for the production of plasticizers, alkyd resins, unsaturated polyester resins and other commercial products.

The commercial production of phthalic anhydride is based on the gas phase oxidation of *o*-xylene, naphthalene, or a mixture of both. The oxidation is performed by feeding a  
15 mixture of the hydrocarbon(s) and an oxygen containing gas, usually air, over a fixed bed of catalyst in a tubular reactor tube at temperatures in the range of 300–400 °C.

Commercially the oxidation is carried out in multitubular fixed-bed reactors. The reaction is exothermic and the heat of reaction is removed by cooling media, usually molten salts, circulating in the shell around the reactor tubes. In spite of the cooling, the reactor is not  
20 isothermal and a temperature profile with a hot spot develops along the tube from inlet to outlet. These local hot spots are undesired because they may damage the catalyst and favour the formation of undesired side products, such as maleic anhydride, benzoic acid, carbon monoxide and carbon dioxide. In order to limit the formation of hot spots, catalyst beds with two or three different catalysts, with graduated activity, are often used. Their  
25 activity is lowest at the entrance of the reactants, where most of the heat is formed, and highest at the outlet of the catalyst bed (US patent 6,362,345). The use of a highly active catalyst, especially in the lower part of the bed, i.e., near the entrance of the reactants, allows to carry out the reaction at lower temperature, with advantages for the yield of the reaction and the life of the catalyst. Therefore it has been very desirable to develop highly  
30 active catalyst compositions which at the same time have a high selectivity for phthalic anhydride.

The catalysts used today for the production of phthalic anhydride are usually supported catalysts wherein the catalytically active material is deposited, preferably as a coating, on an inert support in the form of granules or pellets, usually in the shape of spheres, cylinders or rings. The inert support in the granules or pellets of the catalyst may be, for example,  
5 corundum, steatite, alumina, silicon carbide or any other material having suitable chemical inertness and mechanical and thermal stability. The amount of active material deposited on the inert carrier is usually between 1 and 15 wt.%, based on the total weight of the catalyst.

The active material of the catalysts currently being used in the production of phthalic  
10 anhydride generally comprises titanium dioxide (titania), preferably having the crystalline structure of anatase, vanadium oxide, which is spread over the titanium dioxide and chemically interacts with it, and various additional components which are referred to as dopants. The dopants include elements like cesium, antimony, molybdenum, potassium, phosphorus and mixtures thereof. They are either:

- 15 (i) alkali metal or alkaline earth metal ions, the role of which is claimed to tune the surface acid-basic properties of the catalyst — alkali or alkaline earth metal ions are generally known to increase the selectivity and to decrease the activity of the catalysts (M. S. Wainwright, N. R. Foster, *Catal. Rev.-Sci. Eng.*, **19** (1979) 211; V. Nikolov, D. Klissurski, A. Anastasov, *Catal. Rev. Sci. Eng.*, **33** (1991) 319; C. R. Dias, M. Farinha Portela, G. C. Bond, *Catal. Rev. Sci. Eng.*, **39** (1997) 169) — or  
20 (ii) transition or post-transition metal ions, the role of which is claimed to be the control of the redox properties of vanadium ions (M. S. Wainwright, N. R. Foster, *Catal. Rev.-Sci. Eng.*, **19** (1979) 211; V. Nikolov, D. Klissurski, A. Anastasov, *Catal. Rev. Sci. Eng.*, **33** (1991) 319; C. R. Dias, M. Farinha Portela, G. C. Bond, *Catal. Rev. Sci. Eng.*, **39** (1997) 169); which are considered to be the main active  
25 sites in the reaction.

Another role of dopants can be the stabilization of the morphological features of titanium dioxide, such as crystallinity and surface area, or the formation of compounds with vanadium oxide having peculiar properties.

30 In the oxidation of *o*-xylene or naphthalene, besides phthalic anhydride several by-products are formed, including carbon monoxide, carbon dioxide, *o*-tolualdehyde, *o*-toluic acid, phthalide, maleic anhydride and benzoic acid. In particular, these by-products are formed

in hot spots which can develop in the reactor tubes as described above. These by-products are particularly undesired because they decrease the conversion and the yield of phthalic anhydride and some of them are difficult to remove. In commercial application, the conversion of *o*-xylene must be as high as possible and, consequently, the concentration of unconverted *o*-xylene at the reactor outlet must be as low as possible. Thus the optimal catalyst has to be as active as possible, so to achieve a very high *o*-xylene conversion, and also very selective in phthalic anhydride, leading to as low an amount as possible of by-products.

10 The activity of the catalysts can be increased in different ways:

1) Increasing the surface area of titania, so to achieve a higher dispersion of vanadium active sites (G. Centi, *Appl. Catal., A: general*, 147 (1996) 267, and references cited therein). The main drawback of this approach is that higher surface areas usually result in catalysts which are less resistant towards thermal shocks and local hot-spots, and more easily tend to exhibit recrystallization phenomena with segregation of vanadium oxide, responsible for a decrease of the surface area and progressive decrease of the activity of the catalyst.

2) Loading a higher amount of vanadium oxide while keeping the surface area of titania constant (G. Centi, *Appl. Catal., A: general*, 147 (1996) 267, and references cited therein).

20 The disadvantage of this approach is that it is known that an optimal amount of vanadium exists for a given titanium dioxide surface area, which corresponds to the formation of the so-called "monolayer" of active species. Higher amounts of vanadium oxide are useless and deleterious, since bulk vanadium oxide may form which does not interact with the titanium dioxide and worsens the selectivity of the catalyst towards phthalic anhydride.

25 3) Using suitable dopants to improve the activity of the catalyst while maintaining good performance in terms of selectivity to phthalic anhydride (M. S. Wainwright, N. R. Foster, *Catal. Rev.-Sci. Eng.*, 19 (1979) 211; V. Nikolov, D. Klissurski, A. Anastasov, *Catal. Rev. Sci. Eng.*, 33 (1991) 319; C. R. Dias, M. Farinha Portela, G. C. Bond, *Catal. Rev. Sci. Eng.*, 39 (1997) 169). However, dopants described so far in the literature usually have negative effects on either the activity or the selectivity of the catalyst.

Very few examples of V/Ti/O catalysts for the oxidation of *o*-xylene or naphthalene to phthalic anhydride containing tin as dopant are reported. US Patent 4,469,878 mentions the addition of tin as a promoter:

- (i) tin is added as the sole promoter to a V/Ti/O catalyst, or alternatively is added together with phosphorus;
- (ii) the amount of tin added to the catalyst composition is low: 0.1–1 wt.% of the active components, preferably 0.2–0.6 wt.%.

The performance of the catalyst is not fully satisfactory and in the examples of US Patent 4,469,878 only the oxidation of naphthalene is taken into consideration.

It has been an object of the present invention to provide a catalyst which avoids the disadvantages of the known catalysts for the production of phthalic anhydride and has a very high activity and an excellent selectivity for the formation of phthalic anhydride, especially when *o*-xylene is used as starting material. It has been another object of the invention to provide a simple and economic process for the preparation of said catalyst starting from easily available inexpensive materials. Still another object of the invention has been to provide a process for the production of phthalic anhydride with high conversion of the starting hydrocarbon(s), high yield and high selectivity.

These objects have been accomplished by the catalyst according to claim 1, the process for its preparation according to claim 11 and the process for the production of phthalic anhydride according to claim 15.

Applicants have discovered that the activity of known catalysts can be significantly increased by addition of comparatively large amounts of tin, without any adverse effect on the selectivity to phthalic anhydride. A further finding of the present invention is that the addition of tin is particularly advantageous for the catalyst activity and selectivity if tin is added together with an alkali metal ion, preferably cesium.

The catalysts according to the invention comprise, based on the total weight of the catalytically active oxidic composition (i.e., with disregard of any inert support), from 2 to 15% by weight (calculated as V<sub>2</sub>O<sub>5</sub>) of vanadium and from 1 to 15% by weight (calculated as SnO<sub>2</sub>) of tin. They further comprise from 70 to 97% by weight (calculated as TiO<sub>2</sub>) of

titanium oxide. This means that unless there are additional components (see below), titanium oxide makes up the balance to 100%.

In a preferred embodiment, the catalyst of the invention contains, based on the catalytically active composition, up to 5% by weight (calculated as  $M_2O$ ) of at least one alkali metal. Preferably, the alkali metal is lithium, potassium or rubidium, and more preferably it is cesium.

In an even more preferred embodiment, cesium is present in an amount of from 0.01 to 2% by weight (calculated as  $Cs_2O$ ), based on the catalytically active composition.

In the finished catalyst, the tin is preferably present in the oxidation state +IV.

Preferably, the titanium oxide which forms the basic ingredient of the catalyst of the invention has the anatase structure and a specific surface area of 10 to 30  $m^2/g$ , more preferably 18 to 25  $m^2/g$ .

In a particularly preferred embodiment, the catalyst of the invention contains, based on the catalytically active composition, from 4 to 10% by weight (calculated as  $V_2O_5$ ) of vanadium oxide, from 2 to 7% by weight (calculated as  $SnO_2$ ) of tin oxide and from 0.1 to 0.8% by weight (calculated as  $Cs_2O$ ) of cesium oxide.

In another preferred embodiment, the catalyst of the invention contains one or more element(s) selected from the group consisting of lithium, potassium, rubidium, aluminium, zirconium, iron, nickel, cobalt, manganese, silver, copper, chromium, molybdenum, tungsten, iridium, tantalum, niobium, arsenic, antimony, cerium, phosphorus, and mixtures thereof. These elements may be present in a total amount of up to 5% by weight, based on the catalytically active composition.

Advantageously, the catalyst of the invention comprises an inert support whereon the catalytically active composition is deposited in an amount of from 2 to 15%, preferably 3 to 12% by weight, based on the total weight of the catalyst including the support.

Preferably, the inert support consists of pellets or granules consisting of corundum, steatite, alumina, silicon carbide, silica, magnesium oxide, aluminium silicate, and mixtures thereof.

5 The catalyst of the present invention, which can be used in commercial multitubular reactors, may be prepared according to the following general procedure:

- 1) A mixture of the ingredients (namely: titanium oxide, vanadium oxide and tin oxide and any additional component such as cesium) of the catalyst's active composition, and/or of precursors which can be converted by thermal treatment into said ingredients  
10 is prepared by dissolving, dispersing or suspending said ingredients or precursors in an aqueous or organic solvent, wherein the ingredients and/or precursors are soluble or dispersible.
- 2) If a supported catalyst shall be prepared, the above solution or suspension (slurry) is coated in the form of a thin layer on an inert support and dried or, if an unsupported  
15 catalyst is desired, the solvent contained in the solution or slurry may simply be evaporated and the solid residue dried and/or comminuted, if necessary.
- 3) The coated support or solid residue obtained in the preceding step is subjected to a final thermal treatment to form the definitive active composition.

20 Suitable raw materials for the production of the catalyst include:

TiO<sub>2</sub> in the form of anatase of suitable surface area, preferably between 10 m<sup>2</sup>/g and 30 m<sup>2</sup>/g, more preferably between 18 m<sup>2</sup>/g and 25 m<sup>2</sup>/g;

vanadium(V) oxide or, as a precursor, any vanadium compound which can be converted by heating into vanadium(V) oxide, such as ammonium metavanadate, vanadium chlorides,  
25 vanadium oxychloride, vanadium acetylacetonate and vanadium alkoxides;  
tin dioxide or, as a precursor, tin compounds such as metastannic acid, orthostannic acid, tin oxyhydrates, tin chlorides (stannic or stannous) or tin acetate.

Preferred are tin compounds which are easily soluble or colloiddally dispersible in the medium employed for catalyst preparation.

30 Suitable cesium compounds include cesium sulfate, cesium nitrate, cesium chloride and any other commercial cesium salt or compound.

Suitable inert support are materials such as silica, magnesia, silicon carbide, alumina, aluminium silicate, magnesium silicate (steatite), or other silicates and mixtures thereof. The inert support may be in granular form or in pellet form, usually in the form of spheres, cylinders or rings. The coating of the active compound onto the inert support may be accomplished by spraying the aqueous or organic solution or slurry containing the ingredients and/or precursors on the support. This operation can be carried out in a heated drum, maintained at a temperature which is suitable for the evaporation of the solvent, for example in the range of 50 to 250 °C. The ratio between the amount of support and the amount of solution or slurry, and the amount of components dissolved in the solution or suspended in the slurry, are chosen so to reach the amount of active compound which is finally desired.

The final thermal treatment can be carried out in the heated drum mentioned above, or in a separate oven, or directly in the reactor where the selective oxidation of *o*-xylene, naphthalene or mixtures of the two to phthalic anhydride will take place. The treatment is carried out in air, or other suitable (non-reducing) atmosphere and at a temperature which is typically in the range 250–450 °C.

According to the invention, phthalic anhydride is prepared by oxidizing a hydrocarbon selected from the group consisting of *o*-xylene, naphthalene and mixtures of both in the gas phase at 340 to 400 °C with an oxygen-containing gas, preferably air, in a fixed-bed reactor in the presence of the catalyst of the invention. Advantageously, the oxidation reaction is carried out in a multitubular fixed bed reactor. The catalyst granules are filled into the tubes and the feed prepared by mixing air (or oxygen or any other oxygen-containing gas) with the hydrocarbon (i.e., *o*-xylene and/or naphthalene) is passed over the catalyst bed.

Preferably, the initial concentration (i.e., the concentration in the reactor feed) of the hydrocarbon is between 0.5 and 2 vol.%.

The (gauge) pressure at the reactor inlet is advantageously slightly higher than atmospheric, preferably between 0.35 and 0.55 bar (absolute pressure: ≈1.35–1.55 bar).



The following non-limiting examples and comparative examples describe preferred embodiments of the invention in relation to catalysts according to prior art:

**Example 1 (Comparative Example)**

- 5  $V_2O_5$  (7 wt.%) and  $Cs_2O$  (0.5 wt.%) were deposited on titania (anatase) having a surface area of  $22.5 \text{ m}^2/\text{g}$ . The catalyst was prepared by dissolution of 9.0 g of  $(NH_4)VO_3$  in 2500 ml of hot (60–80 °C) deionized water under stirring. Then  $CsNO_3$  (0.069 g) was dissolved in the same, hot solution. The titania (89.5 g) was dropped in the solution and the resulting slurry was loaded in a rotary evaporator to evaporate the solvent. The wet solid
- 10 was recovered and thermally treated using the following procedure, carried out in static air: Heating from room temperature to 150 °C at a heating rate of 10 K/min; isothermal step at 150 °C for 3 h; then further heating (10 K/min) till a temperature of 450 °C was reached. Final isothermal step at 450 °C for 5 h, and then cooling.

15 **Example 2**

The same procedure as described in Comparative Example 1 was used, except for the addition of 6.65 g of an aqueous tin oxyhydrate sol (Nyacol Co., grade SN15CG) having a tin content equivalent to 15 wt.%  $SnO_2$  and a pH of 10.0. The tin content (as  $SnO_2$ ) in the final catalyst was 1.0 wt.% with respect to the sum of  $SnO_2$ ,  $V_2O_5$  and  $TiO_2$ .

20

**Examples 3–6**

The same procedure as described in Example 2 was used, except for the addition of 20 g, 26.7 g, 33.3 g, and 46.7 g of the  $SnO_2$  sol. The tin content (as  $SnO_2$ ) in the final catalysts was 3.0 wt.%, 4.0 wt.%, 5.0 wt.%, and 7.0 wt.%, respectively.

25

**Example 7 (Comparative Example)**

The same procedure as described in Comparative Example 1 was used, leading to a catalyst with the same composition, except that the surface area of the titania was  $18 \text{ m}^2/\text{g}$ .

**Example 8**

The same procedure as described in Example 4, leading to the same final catalyst composition (i.e., 4.0 wt.% SnO<sub>2</sub>), was used, except that the surface area of the was 18 m<sup>2</sup>/g and SnCl<sub>4</sub> was used as the Sn compound.

**Example 9 (Comparative Example)**

The same procedure as described in Comparative Example 1, leading to a catalyst with the same composition, was used, except that the surface area of the TiO<sub>2</sub> (anatase) was 34 m<sup>2</sup>/g.

**Example 10**

The same procedure as described in Example 4, leading to the same final catalyst composition, was used, except that the surface area of the TiO<sub>2</sub> (anatase) was 34 m<sup>2</sup>/g and the Sn compound was SnCl<sub>4</sub>.

**Catalytic tests**

The procedure for catalytic testing was the following: An upright tubular reactor made from stainless steel, with a diameter of 1.25 cm and 25 cm long was first loaded with 11.1 g of inert material ( $\alpha$ -alumina, 30–60 mesh particles) and then with 0.23 g of catalyst mixed with 1.0 g of the inert material. The catalyst was shaped in granules having a diameter between 30 and 60 mesh. The feed consisted of *o*-xylene vapour (1 vol.%) in air, and the flow rate was such to have a residence time, measured at ambient conditions, of 0.3 s. The pressure was atmospheric.

The results obtained are summarized in Table 1. The selectivities to and yields of phthalic anhydride (PA) are given in mole%. It is evident from these results that:

- (i) the addition of tin in the range examined (1–7 wt.% SnO<sub>2</sub>) results in increased activity,
- (ii) the highest increase of activity is achieved when the amount of Sn is between about 3 and 5 wt.% SnO<sub>2</sub>,
- (iii) that amount of Sn, and specifically an amount corresponding to 3–4 wt.% of SnO<sub>2</sub> also gives a higher maximum yield of PA as compared to a catalyst without tin.

Table 1.

Example No.	T [°C]	Conv. [%]	Sel. PA [%]	Yield PA [%]
Comp. 1	327	26.4	61.1	16.1
	335	39.4	70.6	27.8
	347	61.5	77.0	47.4
	362	78.1	82.0	64.0
	369	86.4	83.3	72.0
	375	99.1	80.6	79.9
2	335	33.8	66.6	22.5
	347	76.1	75.7	57.6
	355	93.8	75.4	70.7
	362	97.4	73.8	71.9
3	315	20.5	54.1	11.1
	325	42.9	65.8	28.2
	335	84.9	78.1	66.3
	345	100	81.3	81.3
4	310	21.3	50.4	10.7
	320	36.2	68.6	24.8
	330	84.6	85.9	72.7
	340	99.2	85.0	84.3
5	315	23.9	54.1	12.9
	325	56.3	68.8	38.7
	335	93.1	73.2	68.1
	345	99.5	71.9	71.5
6	337	46.0	64.9	29.8
	349	75.4	77.4	58.4
	360	99.5	79.8	79.4
	368	100	77.0	77.0
Comp. 7	340	32.5	68.3	22.2
	350	63.8	78.5	50.1
	360	71.9	78.3	56.3
	370	80.9	78.6	63.6
	330	18.0	48.9	8.8
8	339	31.8	61.0	19.4
	355	83.2	79.9	66.5
	365	96.5	81.3	78.5
	371	100	81.5	81.5
	322	23.9	59.8	14.3
Comp. 9	326	46.3	71.0	32.9
	334	76.5	78.9	60.4
	342	89.3	80.7	72.1
	352	99.7	80.1	79.8
	295	4.9	32.4	1.6
10	310	9.6	40.7	3.9
	322	24.2	56.6	13.7
	334	95.8	79.6	76.2
	340	100	81.0	81.0

**Claims**

1. An oxidic catalyst for the production of phthalic anhydride by oxidizing a hydro-carbon selected from the group consisting of *o*-xylene, naphthalene, and mixtures thereof, which catalyst comprises, based on the catalytically active composition, from 2 to 15% by weight (calculated as  $V_2O_5$ ) of vanadium, from 1 to 15% by weight (calculated as  $SnO_2$ ) of tin, from 70 to 97% by weight (calculated as  $TiO_2$ ) of titanium oxide.
2. The catalyst of claim 1 which further contains, based on the catalytically active composition, up to 5% by weight (calculated as  $M_2O$ ) of at least one alkali metal.
3. The catalyst of claim 2 wherein the alkali metal is cesium.
4. The catalyst of claim 3 wherein the cesium is present in an amount of from 0.01 to 2% by weight (calculated as  $Cs_2O$ ), based on the catalytically active composition.
5. The catalyst of any of claims 1 to 4 wherein the tin is present in the oxidation state +IV.
6. The catalyst of any of claims 1 to 5 wherein the titanium oxide has a specific surface area of 10 to 30  $m^2/g$ , preferably 18 to 25  $m^2/g$ , and the anatase structure.
7. The catalyst of any of claims 1 to 6 wherein the catalytically active composition contains from 4 to 10% by weight (calculated as  $V_2O_5$ ) of vanadium oxide, from 2 to 7% by weight (calculated as  $SnO_2$ ) of tin oxide and from 0.1 to 0.8% by weight (calculated as  $Cs_2O$ ) of cesium oxide.
8. The catalyst of any of claims 1 to 7 which further contains at least one element selected from the group consisting of lithium, potassium, rubidium, aluminium, zirconium, iron, nickel, cobalt, manganese, silver, copper, chromium, molybdenum, tungsten, iridium, tantalum, niobium, arsenic, antimony, cerium, phosphorus and mixtures thereof in an amount of up to 5% by weight, based on the catalytically active composition.

9. The catalyst of any of claims 1 to 8 wherein the catalytically active composition is coated on an inert support in an amount of 2 to 15% by weight, preferably 3 to 12% by weight, based on the total weight of the catalyst.

5 10. The catalyst of claim 9 wherein the inert support consists of pellets or granules of at least one material selected from the group consisting of corundum, steatite, alumina, silicon carbide, silica, magnesium oxide, aluminium silicate and mixtures thereof.

10 11. A process for the manufacture of a catalyst according to any one of claims 1 to 10, comprising the steps of  
(i) mixing, in an aqueous or organic solvent, the ingredients of the catalytically active composition and/or precursors of said ingredients, to form a solution or suspension,  
(ii) coating said solution or suspension in the form of a thin layer on an inert support and drying or, if an unsupported catalyst is desired, evaporating the solvent of said  
15 solution or suspension and, optionally, drying and/or comminuting the solid residue and,  
(iii) subjecting the coated support or the solid residue obtained by evaporating the solution or suspension to a thermal treatment to form the definitive catalytically active composition.

20 12. The process of claim 11 wherein the ingredients and/or precursors of the catalytically active composition used to prepare the initial mixture comprise at least one vanadium compound selected from the group consisting of vanadium(V) oxide, ammonium metavanadate, vanadium chlorides, vanadium oxychloride, vanadium acetylacetonate  
25 and vanadium alkoxides, at least one tin compound selected from the group consisting of tin dioxide, metastannic acid, orthostannic acid, tin oxyhydrates, tin chlorides and tin acetate.

30 13. The process of claim 11 or 12 wherein the thermal treatment is conducted at 250 to 400 °C.

14. The process of any of claims 11 to 13 wherein the catalytically active composition is coated on an inert support in granular or pellet form by spraying the solution or

suspension of the ingredients and/or precursors of the catalytically active composition onto said inert support and evaporating the solvent.

5 15. A process for the production of phthalic anhydride comprising the oxidation of a hydrocarbon selected from the group consisting of *o*-xylene, naphthalene and mixtures of *o*-xylene and naphthalene in the gas phase at 340 to 400 °C with an oxygen-containing gas in a fixed-bed reactor in the presence of a catalyst according to any of claims 1 to 10.

10 16. The process of claim 15 wherein the initial concentration of the hydrocarbon in the gas phase is 0.5 to 2.0% by volume.

17. The process of claim 15 or 16 wherein the gauge pressure at the entrance of the reactor is 0.35 to 0.55 bar.

15

## INTERNATIONAL SEARCH REPORT

International Application No

/EP 03/06494

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 B01J23/22 C07C51/31 C07C51/265

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B01J C07C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, COMPENDEX

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DE 19 43 759 A (HEYDEN CHEM FAB) 8 April 1971 (1971-04-08) claims 1-5 example 2	1-17
X	EP 0 985 648 A (NIPPON STEEL CHEMICAL CO) 15 March 2000 (2000-03-15) paragraph [0027] - paragraph [0033] paragraph [0043] - paragraph [0044] table 2	1,5,6, 8-17
X	US 4 469 878 A (KANEYASU MASATAKA ET AL) 4 September 1984 (1984-09-04) cited in the application the whole document	1,5,6, 8-17
A	EP 0 286 448 A (NIPPON STEEL CHEMICAL CO) 12 October 1988 (1988-10-12)	

-/--

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

## \* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

15 September 2003

Date of mailing of the international search report

08.10.2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Zuurdeeg, B

## INTERNATIONAL SEARCH REPORT

International Application No

EP 03/06494

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 4 448 898 A (SUN HSIANG-NING) 15 May 1984 (1984-05-15) -----	



## INTERNATIONAL SEARCH REPORT

International Application No

PCT/JP98/03/06494

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
DE 1943759	A	08-04-1971	DE 1943759 A1	08-04-1971
EP 0985648	A	15-03-2000	AU 4722497 A	15-05-1998
			DE 69722261 D1	26-06-2003
			EP 0985648 A1	15-03-2000
			US 6369240 B1	09-04-2002
			CN 1237951 A	08-12-1999
			WO 9817608 A1	30-04-1998
			KR 2000052776 A	25-08-2000
			TW 415939 B	21-12-2000
			ZA 9709362 A	12-05-1998
US 4469878	A	04-09-1984	JP 1593223 C	14-12-1990
			JP 2018900 B	27-04-1990
			JP 58057331 A	05-04-1983
			JP 1348709 C	28-11-1986
			JP 58057374 A	05-04-1983
			JP 60037108 B	24-08-1985
			GB 2109697 A, B	08-06-1983
			KR 8700919 B1	07-05-1987
EP 0286448	A	12-10-1988	JP 1805573 C	26-11-1993
			JP 5015711 B	02-03-1993
			JP 63253080 A	20-10-1988
			CA 1311740 C	22-12-1992
			CN 1030571 A, B	25-01-1989
			DE 3884441 D1	04-11-1993
			DE 3884441 T2	14-04-1994
			EP 0286448 A2	12-10-1988
			KR 9503117 B1	01-04-1995
			US 4879387 A	07-11-1989
US 4448898	A	15-05-1984	NONE	